




25136 Anza Drive, Valencia, CA 91355 • Tel (661) 295 5920 • Fax (661) 295 5928
 www.Novacap.com E-mail: Info@Novacap.com

NPO RELIABILITY DATA

NPO failure rates at 90% confidence



Test Conditions: 2000hrs. @ 125°C. Applied voltage is dependent on capacitors tested.
Time Period: January 2001 to March 2007.
Number of Capacitors Tested: 10,760
Testing Location: NOVACAP Reliability Test Department
Results: 5 Failures in 1,513,470,800 accelerated unit hours.
Conversion Factors:

From	To	Operation
FITS	MTBF (Hours)	$10^9 / \text{FITS}$
FITS	MTBF (Years)	$10^9 / (\text{FITS} \times 8760)$

⁹
 FITS= Failures in 10⁹ Hours
 MTBF= Mean Time Between Failures